

SKF MPT states that this SDS pertains to the batteries included in the following designations:

> **TLGB 21-2 TLGB 1871**

SKF MPT (Maintenance Products, Power Transmission, Tools & Equipment)

Visiting address: Meidoornkade 14, 3992 AE Houten Delivery address: Peppelkade 68, 3992 AK Houten Mailing address: P.O. Box 2350, 3430 DT Nieuwegein The Netherlands

www.mapro.skf.com

Revision no.: 01



Safety Data Sheet

Regulation: In accordance with Regulation (EU) 2015/830 (REACH), Annex II, and OSHA 29 CFR

1910.1200

Section I – IDENTIFICATION OF THE SUBSTANCE/MIXTURE AND OF THE COMPANY/UNDERTAKING

Important Note: As a solid, manufactured article, exposure to hazardous ingredients is not expected with normal use. This battery is an article pursuant to 29 CFR 1910.1200 and, as such, is not subject to the OSHA Hazard Communication Standard requirement. The information contained in this Safety Data Sheet contains valuable information critical to the safe handling and proper use of the product. This SDS should be retained and available for employees and other users of this product.

1.1 Product identifier

Model name INR18650-25R

Substance name: Lithium-ion batteries

Synonyms:

Lithium-ion Cell, Lithium-ion Battery, Li-Ion Cell, Li-Ion Battery

1.2 Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses: Lithium-ion batteries

Uses advised against: Use for recommended use only

Further Information: Not available

1.3 Details of the supplier of the safety data sheet

Supplier: SAMSUNG SDI Co., Ltd.

Street address/P.O. Box: 150-20, Gongse-ro, Giheung-gu, Yongin-si, Gyeonggi-do, Korea

Country ID/Postcode/Place: KOR/17084

Telephone number: 1-800-424-9300: US and Canada / 1-703-527-3887: International

Responsible Department: Quality team

E-mail address of competent person responsible for the SDS: Not available National contact: 1-800-424-9300: US and Canada / 1-703-527-3887: International

1.4 Emergency Telephone

: 1-800-424-9300: US and Canada / 1-703-527-3887: International

Opening hours: Not available
Other comments: Not available

1.5 Further Information

Battery-System: Lithium-ion (Li-ion)

Nominal Voltage: 3.6 V Rated Capacity: 2.5 Ah Wh rating: 9.0 Wh

Anode (negative electrode): based on intercalation graphite

Cathode (positive electrode): based on lithiated metal oxide (Cobalt, Nickel or Manganese)

Remark:

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019

MODEL INR18650-25R



The information and recommendations set forth are made in good faith and believed to be accurate as of the date of preparation. SAMSUNG SDI Co., Ltd. makes no warranty, expressed or implied, with respect to this information and disclaims all liabilities from reliance on it.

Revision no.: 01

Section II – HAZARDS IDENTIFICATION

* This is a product that fulfills a certain function in solid state with specific shape without dischargin g any chemical substance in its use and has no obligation to write (M)SDS. Since this document co ntains the precautions for safe handling related to its materials or chemical substances consisting of this product, please note that these overall information is irrelevant to this product.

2.1 Classification of the substance or mixture

2.1.1 Classification according to Regulation (EC) No. 1272/2008 [CLP] and OSHA 29 CFR 1910.12

00: Not classified

2.1.2 Additional information:

Classification of the substance or mixture.

Preparation Hazards and Classification: The product is a Lithium ion cell or battery and is therefore classified as an article and is not hazardous when used according to the recommendations of the manufacturer. The hazard is associated with the contents of the cell or battery. Under recommended use conditions, the electrode materials and liquid electrolyte are non-reactive provided that the cell or battery integrity remains and the seals remain intact. The potential for exposure should not exist unless the cell or battery leaks, is exposed to high temperatures or is mechanically, electrically or physically abused/damaged. If the cell or battery is compromised and starts to leak, based upon the battery ingredients, the contents are classified as Hazardous.

Hazardous Materials Information Label (HMIS)

Health: Not available Flammability: Not available Physical Hazard: Not available

NFPA Hazard Ratings

Health: Not available Flammability: Not available Reactivity: Not available

2.2 Label elements

Hazard pictograms: Not applicable

Signal word : Not applicable

Hazard statement : Not applicable

Precautionary statements: Not applicable

Supplemental Hazard information (EU): Not applicable

2.3 Other hazards:

Appearance, Color and Odor: Solid object with no odor.



Primary Routes(s) of Exposure: These chemicals are contained in a sealed enclosure. Risk of exposure occurs only if the cell or pack is mechanically, thermally, electrically or physically abused to the point of compromising the enclosure.

If this occurs, exposure to the electrolyte solution contained within can occur by inhalation, ingestion, eye contact and skin contact.

Potential Health Effect(s):

Acute (short term): see Section 8 for exposure controls.

In the event that this cell or pack has been ruptured, the electrolyte solution contained within the cell would be corrosive and can cause burns to skin and eyes.

Inhalation: Inhalation of materials from a sealed cell is not an expected route of exposure. Vapors or mists from a ruptured cell may cause respiratory irritation.

Ingestion: Swallowing of materials from a sealed cell is not an expected route of exposure.

Swallowing the contents of an open cell can cause serious chemical burns to mouth, esophagus, and gastrointestinal tract.

Skin: Contact between the cell and skin will not cause any harm. Skin contact with the contents of an open cell can cause severe irritation or burns to the skin.

Eye: Contact between the cell and the eye will not cause any harm. Eye contact with the contents of an open cell can cause severe irritation or burns to the eye.

CHRONIC (long term): see Section 11 for additional toxicological data.

Interactions with other chemicals: Immersion in high conductivity liquids may cause corrosion and breaching of the cell or battery enclosure. The electrolyte solution inside of the cells may react with alkaline (basic) materials and present a flammability hazard.

Potential Environmental Effects: Not Available.

Information on whether the substance or mixture meets the criteria for PBT or vPvB : See a section 12.5 of the Safety Data Sheet.

Section III – COMPOSITION/INFORMATION ON INGREDIENTS

3.1 Mixture

CAS No.	EC No.	REACH Registratio n No.	%[weight]	Name	Common Name (Synonyms)	Classification according to Regulation(EC) No 1278/2008(CLP)
12325-84-7	Not available	-	10~20	Litium nickel oxide	Li ₂ NiO ₂	Not classified
7440-44-0	231-153-3	-	10~20	Carbon	Carbon activated	Not classified
7439-89-6	231-096-4	-	10~20	Iron	Fe	Not classified
7440-50-8	231-159-6	-	5~15	Copper	Cu	Acute Tox. 4, H302

Revision no.: 01



SAMSUNG SDI

	1	ı	1	T		P 1 1 2 2 1 2 1 2 1 2 1 2 1 2 1 2 1 2 1
						Eye Irrit. 2, H319
						Acute Tox. 3, H331
						Aquatic Acute 1, H400
						Aquatic Chronic 1, H410
						Skin Sens. 1, H317
12031-65-1	620-400-4	_	1~10	Lithium nickel dioxide	Lithium nickelate	STOT RE 1. H372 **
12001 00 1	020 100 1		' '	Emilam monor dioxido	Litinam monolato	Carc. 1A, H350i
						·
						Pyr. Sol. 1, H250
						Water-react. 2,
7429-90-5	231-072-3	-	1~10	Aluminium	Al	H261(pyrophoric)
1429-90-3	231-072-3			Aiuminium		Flam. Sol. 1, H228
						Water-react. 2,
						H261(stabilised)
12190-79-3	235-362-0	-	1~10	Cobalt lithium dioxide	Lithium cobaltite	Not classified
					Carbonic acid	
616-38-6	210-478-4	-	1~10	Dimethyl carbonate	dimethyl ester	Flam. Liq. 2, H225
12057 17 0	604 704 5		1~10	Lithium Manganese (III,IV)	LiMp O	Not algorified
12057-17-9	601-724-5	-	1~10	oxide	LiMn ₂ O ₄	Not classified
					Ethene,	
9002-88-4	618-339-3	-	1~10	Polyethylene	homopolymer	Not classified
96-49-1	202-510-0		1~3	Ethylene carbonate	1,3-Dioxolan-2-one	Not classified
30-43-1	202-310-0	-	1-5	Littylerie carbonate		Not classified
0.100.1.10.0				Lithium	ithium	
21324-40-3	244-334-7	-	1~3	hexafluorophosphate(1-)	hexafluorophospha	Not classified
				nexandoropriospriate(1)	te	
7782-42-5	231-955-3	-	1~3	Graphite	Grafito	Not classified
623-53-0	433-480-9	-	1~3	Ethyl methyl carbonate	EMC	Not classified
Trade secret	Not available	_	0.1~0.99	Trade secret 1	Gasket material	Not classified
	1101 01010010		011 0100		- Cacher Haterian	Skin Sens. 1, H317
7440-02-0	231-111-4	-	0.1~0.99	Nickel	Ni	Carc. 2 ,H351
						STOT RE 1, H372
						Aquatic Chronic 3, H412
				1,4-Benzenedicarboxylic		
				acid, 1,4-dimethyl ester,		
25640-14-6	607-767-6	-	0.1~0.99	polymer with 1,4-	1,2 ethanediol	Not classified
				cyclohexanedimethanol		
				and 1,2-ethanediol		
9003-07-0	618-352-4	_	0.1~0.99	1-Propene, homopolymer	Polypropylene	Not classified
,,,,,,			111 0.00		,,-,,	Skin Irrit. 2, H315
					1 mothylpyrrolidin	Eye Irrit. 2, H319
872-50-4	212-828-1	_	0.3~0.99	1-methyl-2-pyrrolidone	1-methylpyrrolidin-	
					2-one	STOT SE 3, H335
						Repr. 1B, H360D***
						Skin Sens. 1, H317
	I	I				Muta. 2, H341
		1				
40040 54 7	040.044.0		0.4.0.00	Nicoland and shirts	NU alaal aa aa aa aa de da	STOT RE 1, H372 **
16812-54-7	240-841-2	-	0.1~0.99	Nickel sulphide	Nickel monosulfide	
16812-54-7	240-841-2	-	0.1~0.99	Nickel sulphide	Nickel monosulfide	Aquatic Acute 1, H400
16812-54-7	240-841-2	-	0.1~0.99	Nickel sulphide	Nickel monosulfide	Aquatic Acute 1, H400 Aquatic Chronic 1, H410
16812-54-7	240-841-2	-	0.1~0.99		Nickel monosulfide	Aquatic Acute 1, H400
16812-54-7	240-841-2	-	0.1~0.99	Poly[N,N'-(1,4-phenylene)-	Nickel monosulfide	Aquatic Acute 1, H400 Aquatic Chronic 1, H410
16812-54-7 26023-21-2	240-841-2 631-079-5	-	0.1~0.99	Poly[N,N'-(1,4-phenylene)- 3,3',4,4'-	Nickel monosulfide	Aquatic Acute 1, H400 Aquatic Chronic 1, H410
		-		Poly[N,N'-(1,4-phenylene)- 3,3',4,4'- benzophenonetetracarboxy		Aquatic Acute 1, H400 Aquatic Chronic 1, H410 Carc. 1A, H350i
		-		Poly[N,N'-(1,4-phenylene)- 3,3',4,4'-		Aquatic Acute 1, H400 Aquatic Chronic 1, H410 Carc. 1A, H350i Not classified
26023-21-2	631-079-5	-	0.1~0.99	Poly[N,N'-(1,4-phenylene)- 3,3',4,4'- benzophenonetetracarboxy lic imide/amic acid]	Imide resin	Aquatic Acute 1, H400 Aquatic Chronic 1, H410 Carc. 1A, H350i Not classified Acute Tox. 3 *, H301
		-		Poly[N,N'-(1,4-phenylene)- 3,3',4,4'- benzophenonetetracarboxy		Aquatic Acute 1, H400 Aquatic Chronic 1, H410 Carc. 1A, H350i Not classified Acute Tox. 3 *, H301 Acute Tox. 3 *, H311
26023-21-2	631-079-5	-	0.1~0.99	Poly[N,N'-(1,4-phenylene)- 3,3',4,4'- benzophenonetetracarboxy lic imide/amic acid]	Imide resin	Aquatic Acute 1, H400 Aquatic Chronic 1, H410 Carc. 1A, H350i Not classified Acute Tox. 3 *, H301

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019

MODEL INR18650-25R



SAMSUNG SDI

554-13-2	209-062-5	-	0.1~0.99	Lithium carbonate	Carbonic acid, dilithium salt	Not classified
1333-86-4	215-609-9	-	0.1~0.99	Carbon black	Carbon	Not classified
9003-55-8	618-370-2	-	0.1~0.99	1,3 Butadiene/styrene copolymers	Styrene, butadiene copolymer	Not classified
26337-35-9	Not available	-	0.1~0.99	Acetic acid ethenyl ester, polymer with carbon monoxide and ethene	Not available	Not classified
9004-32-4	618-378-6	-	0.1~0.99	Carboxymethyl cellulose sodium salt	Cellulose, carboxymethyl ether, sodium salt	Not classified
110-61-2	203-783-9	-	0.1~0.99	Succinonitrile	Butanedinitrile	Not classified
11089-89-7	Not available	-	0.1~0.99	Aluminum lithium oxide (AlLiO)	Not available	Not classified

Further Information

Because of the cell structure the dangerous ingredients will not be available if used properly. During charge process a lithium graphite intercalation phase is formed.

Revision no.: 01

Section IV - FIRST-AID MEASURES

4.1 Description of first aid measures

Following eye contact:

- Rinse eyes with plenty of water for at least 15 minutes and seek medical attention.

Following skin contact:

- Remove contaminated clothing and wash before reuse.
- Immediately rinse contact area with plenty of clean water.
- Provide first aid to contacted area to prevent infection.
- Get medical attention.

Following inhalation:

- In case of inhalation of organic electrolyte mist, remove from exposure to fresh air.
- If necessary give oxygen. Get medical attention.

Following ingestion:

- In case of ingestion of electrolyte don't induce vomiting.
- If patient is conscious and alert give 2~4 cupfuls of milk or water.
- Never give anything by mouth to an unconscious person.
- Get medical attention immediately.

Further Information:

- The following first aid measures are required only in case of exposure to interior battery components after damage of the external battery casing.
- Undamaged, closed cells do not represent a danger to the health.

4.2 Most important symptoms and effects, both acute and delayed

Acute effects: Not available Delayed effects: Not available

4.3 Indication of immediate medical attention and special treatment needed

Revision no.: 01



- Ensure that medical personnel are aware of the material(s) involved and take precautions to protect themselves.

Section V - FIRE-FIGHTING MEASURES

5.1 Extinguishing media

- When the scale of the fire is small, use a HFC (hydrofluorocarbon) clean-agent fire extinguisher or alcohol resistant foam fire extinguishers. (In case of battery overheating, wear protective gear and immerse heated battery in water)
- In case of large fire, use large amount of water to extinguish.

5.2 Special hazards arising from the substance or mixture

- Flammable gas leaks before ignition and then the product ignites.

5.3 Advice for firefighters

- The ignited battery has a high temperature, so there is a risk of additional ignition even if the fire is extinguished at early stage. Sprinkle a large amount of water until the battery temperature drops to normal temperature.
- If the battery is ignited in multi-stacked condition, multi-stack should be disassembled and then extinguished so that heat is not transferred between batteries
- In the event of a battery fire, cool it by spraying water directly on the battery.
- When handling a overheated battery, wear heat-resistant protective equipment.

Section VI - ACCIDENTAL RELEASE MEASURES

6.1 Personal precautions, protective equipment and emergency procedures

For non-emergency personnel

Protective equipment : Use personal protective equipment, see Section 8

Emergency procedures:

- In case of cell damage, possible release of dangerous substances and a flammable gas mixture.
- Eliminate all ignition sources.
- Please note that materials and conditions to avoid.
- Battery may emit electrolyte if charging or discharging rates exceed manufacturer's recommendations or if pack has been breached.
- Move battery to well ventilated area to prevent gas accumulation.

For emergency responders

- Eliminate all ignition sources.
- Please note that materials and conditions to avoid.
- Move battery to well ventilated area to prevent gas accumulation.

6.2 Environmental precautions:

- Avoid release to the environment.
- Prevent entry into waterways, sewers, basements or confined areas.

6.3 Methods and material for containment and cleaning up

For containment: Not available

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019

MODEL INR18650-25R



SAMSUNG SDI

For cleaning up:

- Cover with Dry earth, DRY sand or other non-combustible material and put on the plastic sheet to minimize spreading or contact with rain.
- Move battery to well ventilated area to prevent gas accumulation.
- Dispose in accordance with applicable local, state and federal regulations.

Revision no.: 01

Other information: Not available

6.4 Reference to other sections

- See also sections 8 and 13 of the Safety Data Sheet.

Section VII - HANDLING AND STORAGE

7.1 Precautions for safe handling

- In case of cell damage, possible release of dangerous substances and a flammable gas mixture.
- The battery stores electrical energy and is capable of rapid energy discharge.
- Battery cell contents are under pressure.
- Handle battery carefully to avoid puncturing case or electrically shorting terminals.

7.2 Conditions for safe storage, including any incompatibilities

Technical measures and storage conditions: Not available

Packaging materials: Not available

Requirements for storage rooms and vessels:

- Storage at room temperature (approx. 20°C) at approx. 40% of the nominal capacity
- Keep in closed original container.

7.3 Specific end use(s)

Recommendations: Not available

Industrial sector specific solutions: Not available

Section VIII – EXPOSURE CONTROLS / PERSONAL PROTECTION

8.1 Control parameters

Occupational Exposure limits

Name	ACGIH regulation	Biological exposure index	OSHA regulation	NIOSH regulation	EU regulation
Litium nickel oxide	TWA = 0.2 mg/m³ (Nickel insoluble ino rganic compounds), TWA = 0.1 mg/m³ (Nickel soluble inorg anic compounds)	Not available	Not applicable	Not applicable	Not applicable
Carbon	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Iron	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Copper	TWA = 0.2 mg/m^3	Not available	TWA = 1 mg/m^3 (ot	TWA = 1 mg/m^3 (ot	Not applicable

Revision no.: 01



SAMSUNG SDI

	(fume)		her conner compoun	her copper compoun	
	(Turrie)			ds (as Cu) except c	
			opper fume)	opper fume)	
Lithium nickel dioxide	TWA = 0.2 mg/m³ (Nickel insoluble ino rganic compounds), TWA = 0.1 mg/m³ (Nickel soluble inorg anic compounds)	Not available	Not applicable	Not applicable	Not applicable
Aluminium	TWA = 1 mg/m³ (re spirable particulate matter)	Not available	TWA = 10 mg/m³ (Total dust), 5 mg/m³ (Respirable fraction)	TWA = 10 mg/m³ (Total dust), 5 mg/ m³ (Respirable fracti on)	Not applicable
Cobalt lithium dioxide	TWA = 0.02 mg/m³ (Cobalt inorganic compounds, as Co)	Not available	Not applicable	Not applicable	Not applicable
Dimethyl carbonate	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Lithium Manganese (III,IV) oxide	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Polyethylene	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Ethylene carbonate	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Lithium hexafluorophosp hate(1-)	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Graphite	TWA = 2 mg/m ³	Not available	TWA = 15 mppcf (mineral dusts)	TWA = 2.5 mg/m ³ (resp)	Not applicable
Ethyl methyl carbonate	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Trade secret 1	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Nickel	TWA = 1.5 mg/m³ (i nhalable particulate matter)	Not available	TWA = 1 mg/m ³	Ca TWA = 0.015 m g/m^3	Not applicable
1,4- Benzenedicarboxylic acid , 1,4- dimethyl ester, polymer w ith 1,4- cyclohexanedimethanol a nd 1,2-ethanediol	Not applicable	Not available	Not applicable	Not applicable	Not applicable
1-Propene, homopolymer	Not applicable	Not available	Not applicable	Not applicable	Not applicable
1-methyl-2-pyrrolidone	Not applicable	Not available	Not applicable	Not applicable	TWA = 10 ppm (40 mg/m ³), STEL = 20 ppm (80 mg/m ³)
Nickel sulphide	TWA = 0.1 mg/m³ (Nickel soluble inorg anic compounds), 0. 2 mg/m³ (Nickel ins oluble inorganic compounds)	Not available	Not applicable	Not applicable	Not applicable
Poly[N,N'-(1,4- phenylene)-3,3',4,4'- benzophenonetetracarbo xylic imide/amic acid]	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Silicon	Not applicable	Not available	TWA = 10 mg/m ³ (Total dust), TWA =	TWA = 10 mg/m ³ (t otal) TWA = 5 mg/	Not applicable

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019

MODEL INR18650-25R



SAMSUNG SDI

			5 mg/m³ (Respirable	m³ (resp)	
			fraction)		
Trade secret 2	Not applicable	Not available	Not available	Not available	Not applicable
Lithium carbonate	Not applicable	Not available	Not available	Not available	Not applicable
Carbon black	TWA = 3 mg/m³ (in halable particulate matter)	Not available	TWA = 3.5 mg/m ³	TWA = 3.5 mg/m³, TWA = 0.1 mg/m³ (Carbon black in pr esence of Polycyclic aromatic hydrocarb ons, as PAH)	Not applicable
1,3 Butadiene/styrene co polymers	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Acetic acid ethenyl ester, polymer with carbon mon oxide and ethene	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Carboxymethyl cellulose sodium salt	Not applicable	Not available	Not applicable	Not applicable	Not applicable
Succinonitrile	Not applicable	Not available	Not applicable	TWA = 6 ppm (20 mg/m ³)	Not applicable
Aluminum lithium oxide (AlLiO)	TWA = 1 mg/m³ (re spirable particulate matter)(Aluminum in soluble compounds)	Not available	Not applicable	Not applicable	Not applicable

Revision no.: 01

8.2 Exposure controls

8.2.1 Appropriate engineering controls :

Substance/mixture related measures to prevent exposure during identified uses:

- Avoid charging batteries in areas where hydrogen gas accumulate.
- Use local exhaust ventilation to maintain concentrations of hydrogen below the Lower Explosive collect and transport flammable gases in ventilation systems.
- Insure proper ventilation is present and electrolyte mist and vapours.

Structural measures to prevent exposure:

- Avoid charging batteries in areas where hydrogen gas accumulate.
- Use local exhaust ventilation to maintain concentrations of hydrogen below the Lower Explosive collect and transport flammable gases in ventilation systems.
- Insure proper ventilation is present and electrolyte mist and vapours.

Organisational measures to prevent exposure: Not available

Technical measures to prevent exposure:

- Insure proper ventilation is present and electrolyte mist and vapours.

8.2.2 Individual protection measures, such as personal protective equipment:

Eye and face protection

- Wear ANSI approved safety glasses with side shield during normal use.
- Wear NIOSH approved face shield with safety glasses and H.V protection during intentional disassembly.

Skin protection

Hand protection

- Wear nitrile butyl rubber, neoprene, or PVC glove during battery component disassembly.
- Discard contaminated work clothing after one work day.

Other skin protection

SAMSUNG SDI Co., Ltd.

Date: Jan 1st, 2019 Revision no.: 01



- Wear protective clothing during battery component disassembly.
- Discard contaminated work clothing after one work day.

Respiratory protection:

MODEL INR18650-25R

- None required during normal use.
- Wear NIOSH or European Standard EN 149 approved full or half face piece (with goggles) respiratory protective equipment when necessary.
- In lack of oxygen(< 19.5%), wear the supplied-air respirator or self-contained oxygen breathing apparatus.
- In case exposed to particulate material, the respiratory protective equipment as follow are recommended; facepiece filtering respirator or air-purifying respirator, high-efficiency particulate air(HEPA) filter media or respirator equipped with powered fan, filter media of use (dust, mist, fume)

8.2.3 Environmental exposure controls

Substance/mixture related measures to prevent exposure: Not available

Instruction measures to prevent exposure: Not available
Organizational measures to prevent exposure: Not available
Technical measures to prevent exposure: Not available

Section IX – PHYSICAL AND CHEMICAL PROPERTIES

9.1 Information on basic physical and chemical properties

Appearance

Description: Solid **Color**: Not available

Odor: Odorless

Odor threshold: Not available

pH: Not available

Melting point/freezing point: Not available

Initial boiling point and boiling range: Not available

Flash point : Not available Evaporation rate : Not available

Flammability (solid, gas): Not available

Upper/lower flammability or explosive limits : Not available

Vapor pressure: Not available Solubility (ies): Not available Vapor density: Not available Relative density: Not available

Partition coefficient: n-octanol/water: Not available

Auto ignition temperature: Not available **Decomposition temperature**: Not available

Viscosity: Not available

Explosive properties : Not available Oxidizing properties : Not available Molecular weight : Not available

Revision no.: 01

SAMSUNG SDI

9.2 Other information

: Not available

Section X – STABILITY AND REACTIVITY

10.1 Reactivity

- Stable at ambient temperature.

10.2 Chemical stability

- There is no hazard when the measures for handling and storage are followed.
- Stable under normal temperatures and pressures.

10.3 Possibility of hazardous reactions

- Will not occur under normal conditions.
- In case of cell damage, possible release of dangerous substances and a flammable gas mixture.
- Containers may explode when heated.
- Fire may produce irritating and/or toxic gases.
- Inhalation of material may be harmful.

10.4 Conditions to avoid

- Keep away from heat/sparks/open flames/hot surfaces. No smoking.
- Friction, heat, sparks or flames
- Dusts or shavings from borings, turnings, cuttings, etc.
- Do not exceed manufacturer's recommendation for charging or use battery for an application for which it was not specifically designed.
- Do not electrically short.

10.5 Incompatible materials

- Avoid contact with acids and oxidizers.
- Keep away from any possible contact with water, because of violent reaction and possible flash fire.
- Handle under inert gas. Protect from moisture.
- Combustibles, reducing agents

10.6 Hazardous decomposition products

- None under normal conditions.
- Corrosive and/or toxic fume
- Material may produce irritating and highly toxic gases from decomposition by heat and combustion during burning.
- Irritating and/or toxic gases

Section XI – TOXICOLOGICAL INFORMATION

* This is a product that fulfills a certain function in solid state with specific shape without dischargin g any chemical substance in its use and has no obligation to write (M)SDS. Since this document co ntains the precautions for safe handling related to its materials or chemical substances consisting of this product, please note that these overall information is irrelevant to this product.

Revision no.: 01



11.1 Information on toxicological effects

Acute toxicity

Oral: Not classified (ATEmix = 1001 mg/kg bw)

- Carbon : Rat LD₅₀ > 2000 mg/kg (OECD Guideline 423, GLP)
- Iron : Rat LD_{50} = 98600 mg/kg (OECD Guideline 401, GLP)
- Copper: Rat LD₅₀ = 481 mg/kg (OECD Guideline 401, GLP)
- Aluminium : Rat LD₅₀ > 15900 mg/kg (Read-across)(OECD Guideline 401)
- Cobalt lithium dioxide: Rat LD₅₀ > 5000 mg/kg (OECD Guideline 425, GLP)
- Dimethyl carbonate : Rat LD₅₀ > 5000 mg/kg (male/female)(OECD Guideline 401, GLP)
- Polyethylene : Rat LD₅₀ > 2000 mg/kg
- Ethylene carbonate : Rat LD₅₀ = 10400 mg/kg (OECD Guideline 401)
- Lithium hexafluorophosphate(1-): Rat LD₅₀ = 50~300 mg/kg (OECD Guideline 423, GLP)
- Graphite: Rat LD₅₀ > 2000 mg/kg (OECD Guideline 423, GLP)
- Ethyl methyl carbonate : Rat LD₅₀ > 5000 mg/kg (OECD Guideline 401, GLP)
- Nickel: Rat LD₅₀ > 9000 mg/kg (OECD Guideline 401, GLP)
- 1-methyl-2-pyrrolidone : Rat LD₅₀ = 4150 mg/kg (OECD Guideline 401)
- Nickel sulphide: Rat LD₅₀ > 5000 mg/kg (OECD Guideline 401, GLP)
- Silicon: Rat LD₅₀ > 5000 mg/kg (OECD Guideline 401, GLP)
- Trade secret 2 : Rat LD₅₀ = ca. 500 mg/kg (OECD Guideline 423, GLP)
- Lithium carbonate : Rat LD₅₀ = 525 mg/kg
- Carbon black : Rat LD_{50} > 10000 mg/kg (OECD Guideline 401, GLP)
- Carboxymethyl cellulose sodium salt : Rat LD_{50} = 27000 mg/kg (Food Research. Vol. 13, Pg. 29, 1948.)
- Succinonitrile: Rat LD₅₀ = 300~2000 mg/kg (OECD Guideline 423, GLP)

Dermal: Not classified (ATEmix = 26400 mg/kg bw)

- Copper : Rat LD₅₀ > 2000 mg/kg (OECD Guideline 402, GLP)
- Cobalt lithium dioxide : Rat LD_{50} > 2000 mg/kg (OECD Guideline 402, GLP)
- Dimethyl carbonate : Rabbit LD₅₀ > 2000 mg/kg (male/female)(GLP)
- Ethylene carbonate: Rat LD₅₀ = 2000 mg/kg (male/female)(OECD Guideline 402, GLP)
- 1-methyl-2-pyrrolidone : Rat $LD_{50} > 5000$ mg/kg (OECD Guideline 402)
- Silicon : Rabbit LD₅₀ > 5000 mg/kg
- Trade secret 2 : Rat LD₅₀ > 2000 mg/kg (OECD Guideline 402, GLP)
- Lithium carbonate: Rabbit LD₅₀ > 3000 mg/kg (OECD Guideline 402, GLP)
- Succinonitrile: Rat LD₅₀ > 2000 mg/kg (OECD Guideline 402, GLP)

Inhalation: Not classified (ATEmix = 95.45 mg/L)

- Carbon : Rat LC₀ = 8.5 mg/L / 1 hr (OECD Guideline 403)
- Iron : Rat LC_{50} > 100 mg/m³ / 6 hr (carbonyl iron)
- Copper: Rat LC₅₀ > 5.11 mg/L / 4 hr (OECD Guideline 436, GLP)
- Aluminium : Rat LC₅₀ > 0.888 mg/L / 4 hr (OECD Guideline 403)
- Dimethyl carbonate: Rat LC₅₀ > 5.36 mg/L / 4 hr (male/female)(OECD Guideline 403, GLP)
- Ethylene carbonate: Rat LC₀ = 730 mg/m³ / 8 hr (male/female)(OECD Guideline 403)
- Graphite: Rat LC₅₀ > 2000 mg/m³ / 4 hr (OECD Guideline 403, GLP)
- Ethyl methyl carbonate : Rat LC_{50} > 17.6 mg/L / 4 hr (OECD Guideline 403, GLP)
- 1-methyl-2-pyrrolidone : Rat LC₅₀ > 5.1 mg/L / 4 hr (OECD Guideline 403)

Revision no.: 01



- Nickel sulphide : Rat LC_{50} = 0.924 mg/L / 4 hr (OECD Guideline 403, GLP) (Read-across; Nickel subsulfide)
- Lithium carbonate : Rat LC₅₀ > 2 mg/L / 4 hr (OECD Guideline 403, GLP)
- Carbon black : Rat LC₀ = 4.6 mg/m³ / 4 hr (OECD Guideline 403)
- Carboxymethyl cellulose sodium salt : Rat $LC_{50} > 5800 \text{ mg/m}^3 / 4 \text{ hr}$ (Toxicology Letters. Vol. (Suppl), Pg. 243, 1992.)
- Succinonitrile : Rat $LC_{50} \ge 2.67 \text{ mg/L} / 4 \text{ hr (OECD Guideline 403)}$

Skin corrosion/irritation: Not classified

- Carbon : In the skin irritation test using rabbits, the test material was not irritating. (OECD Guideline 404, GLP)
- Iron : In the skin irritation test using rabbits, the test material was not irritating. (OECD Guideline 404, GLP) (Fe_2O_3 83.5 %, FeO 12%, Co 4.5%)
- Copper : In the skin irritation test using rabbits, the test material was not irritating. (OECD Guideline 404. GLP)
- Aluminium : In the skin irritation test using rabbits, the test material was not irritating. (Readacross)(OECD Guideline 404)
- Cobalt lithium dioxide : In in vitro skin irritation test, the test material was not irritating. (OECD Guideline 439)
- Dimethyl carbonate: In the skin irritation test using rabbits, the test material was not irritating. (OECD Guideline 404)
- Polyethylene: In the skin irritation test using rabbits, the test material was mildly irritating.
- Ethylene carbonate : In the skin irritation test using rabbits, the test material was not classified. (OECD Guideline 404, GLP)
- Lithium hexafluorophosphate(1-): In the skin irritation test using human skin model, the test material was corrosive. (EU Method B.40, GLP)
- Graphite : In the skin irritation test with rabbits, the test material was not irritating. (OECD Guideline 404, GLP)
- Ethyl methyl carbonate : In the skin irritation test using rabbits, the test material was not irritating. (OECD Guideline 404, GLP)
- Nickel: Industrial nickel dust causes nickel dermatitis.
- 1-Propene, homopolymer: Processes involved in production&processing of polyolefins are usually totally enclosed & type of accidents that may occur will be burns to skin or eyes, or asphyxiation or intoxication due to inhalation of vapors escaping from leaks.
- 1-methyl-2-pyrrolidone : In the skin irritation test using rabbits, the test material was not irritating. (OECD Guideline 404)
- Nickel sulphide: In the skin irritation test using rabbits, the test material was slightly irritating. The mean erythema score is 0.3 at 24 and 48h, and 0 at 72h. The effects are fully reversible within 72 hours. (OECD Guideline 404, GLP) (Read-across; Nickel subsulfide)
- Silicon : In the skin irritation test using rabbits, the test material was not irritating. (OECD Guideline 404, GLP)
- Trade secret 2 : In the skin irritation test using human skin model, the test material was irritating. (OECD Guideline 439, GLP)
- Lithium carbonate : In the skin irritation test using rabbits, the test material was not irritating. (OECD Guideline 404, GLP)

SAMSUNG SDI Co., Ltd.

Date: Jan 1st, 2019 Revision no.: 01

MODEL INR18650-25R



- Carbon black : In the skin irritation test using rabbits, the test material was not classified. (OECD Guideline 404)
- Succinonitrile : In the skin irritation test using rabbits, the test material was not irritating. (OECD Guideline 404)

Serious eye damage/ irritation : Not classified

- Carbon: In the eyes irritation test with rabbits, the test material was slightly irritating. but they were fully reversible within 7 days. (OECD Guideline 405, GLP)
- Iron: In the eye irritation test using rabbits, the test material was not irritating. (OECD Guideline 405)
- Copper: In the eyes irritation test with rabbits, the test material was irritating. but it was fully reversible within 7 days. (OECD Guideline 405, GLP)
- Aluminium : In the eye irritation test using rabbits, the test material was not irritating. (Read-across)
- Cobalt lithium dioxide : In the eye irritation test using rabbits, the test material was not irritating. (OECD Guideline 405, GLP)
- Dimethyl carbonate: In the eye irritation test using rabbits, the test material was not irritating. (GLP)
- Polyethylene: In the eye irritation test using rabbits, the test material was mildly irritating.
- Ethylene carbonate : In the eye irritation test using rabbits, the test material was mildly irritating. (OECD Guideline 405, GLP)
- Lithium hexafluorophosphate(1-): In the eye irritation test using fertilised brown leghorn chicken eggs, the test material was severely irritating. (GLP)
- Graphite : In the eyes irritation test with rabbits, the test material was slightly irritating. it was fully reversible within 7 days. (OECD Guideline 405, GLP)
- Ethyl methyl carbonate : In the eye irritation test using rabbits, the test material was not irritating. (OECD Guideline 405, GLP)
- Nickel: In the eyes irritation test with rabbits, the test material was slightly irritating. but they were fully reversible within 7 days. (OECD Guideline 405, GLP)
- 1-methyl-2-pyrrolidone: In the eye irritation test using rabbits, the test material was irritating. Moderate ocular effects observed, but Corneal and conjunctival effects were reversible within 14 days and 21 days, respectively. (OECD Guideline 405)
- Nickel sulphide: In the eye irritation test using rabbits, the test material was mildly irritating. the effects are fully reversible within 72 hours. (OECD Guideline 405, GLP) (Read-across; Nickel subsulfide)
- Silicon: In the eye irritation test using rabbits, the test material was not irritating. (OECD Guideline 405, GLP) (Read-across; Silica, precipitated, cryst.-free; CAS-No.: 112926-00-8)
- Lithium carbonate: In the eyes irritation test with rabbits, the moderate conjunctivitis was observed. but they were fully reversible within 7 days. (conjunctivae score 2,2,1.3,1/3)(OECD Guideline 405, GLP)
- Carbon black : In the eye irritation test using rabbits, the test material was not irritating. (OECD Guideline 405)
- Succinonitrile: In the eye irritation test using rabbits, the test material was not irritating. The group mean 24, 48, 72-hour scores were 0 for corneal opacity, 0 for iritic effect and 0.07 for chemosis(fully reversible within 7 days). (OECD Guideline 405)

Respiratory sensitization: Not classified

- Aluminium: In the respiratory sensitization test using mice, the test material was not respiratory sensitization. (Read-across)
- Carbon black: This material has not been tested in animals for sensitization effects on the respiratory tract. In humans, no cases of allergies were reported to the responsible occupational physicians.

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019

MODEL INR18650-25R

SAMSUNG

SAMSUNG SDI

Skin sensitization: Not classified

- Carbon: In the skin sensitization test using mice, the test material was not skin sensitizing. (OECD Guideline 429, GLP)
- Iron: In the skin sensitization test using guinea pigs, the test material was not skin sensitizing. (FeO.Fe₂O₃)

Revision no.: 01

- Copper: In the skin sensitization test using guinea pigs, the test material was not skin sensitizing. (OECD Guideline 406, GLP)
- Aluminium: In the skin sensitization test using guinea pigs, the test material was not skin sensitizing.
- Cobalt lithium dioxide: In the skin sensitization test using mice, the test material was not skin sensitizing. (OECD Guideline 429, GLP)
- Dimethyl carbonate: In the skin sensitization test using guinea pigs, the test material was not skin sensitizing. (OECD Guideline 406, GLP)
- Polyethylene: In the skin sensitization test using guinea pigs, the test material was not skin sensitizina.
- Ethylene carbonate: In the skin sensitization test using guinea pigs, the test material was not classified. (OECD Guideline 406, GLP)
- Lithium hexafluorophosphate(1-): In the skin sensitization test using mice, the test material was not skin sensitizing. (OECD Guideline 429, GLP)
- Graphite: In the skin sensitization test using mice, the test material was not skin sensitizing. (OECD Guideline 429, GLP)
- Ethyl methyl carbonate: In the skin sensitization test using guinea pigs, the test material was not skin sensitizing. (OECD Guideline 406, GLP)
- Nickel: Nickel hypersensitivity dermatitis may be initiated by contact with nickel on the skin.
- 1-methyl-2-pyrrolidone: In the skin sensitization test using mice, the test material was not skin sensitizing. (OECD Guideline 429, GLP)
- Nickel sulphide: In the skin sensitization test using quinea pigs, the test material was skin sensitising. Mean erythema score at 24 and 48 hours were 1.1 and 1.0, respectively. (Guinea pig mazimization test, GLP) (Read-across)
- Trade secret 2: In the skin sensitization test using mouse, the test material was skin sensitizing. (OECD Guideline 429, GLP)
- Lithium carbonate: In the skin sensitization test using guinea pigs, the test material was not skin sensitizing. (OECD Guideline 406, GLP)
- Carbon black: In the skin sensitization test using guinea pigs, the test material was not skin sensitizing. (OECD Guideline 406, GLP)
- Succinonitrile: In the skin sensitization test using mice, the test material was not skin sensitizing. (OECD Guideline 429, GLP)

Carcinogenicity: Not classified

- Litium nickel oxide

IARC: Group 1 (Nickel compounds)

NTP: R (Nickel compounds)

OSHA: Present (Nickel compounds)

ACGIH: A1 (Nickel insoluble inorganic compounds), A4 (Nickel soluble inorganic compounds) KOREA-ISHL: Carcinogenicity1A (Nickel(soluble compounds, insoluble inorganic compounds), CAS No.7440-02-0)

- Lithium nickel dioxide

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019

MODEL INR18650-25R

SAMSUNG

SAMSUNG SDI

IARC: Group 1 (Nickel compounds)

NTP: R (Nickel compounds)

OSHA: Present (Nickel compounds)

ACGIH: A1 (Nickel insoluble inorganic compounds), A4 (Nickel soluble inorganic compounds) KOREA-ISHL: Carcinogenicity1A (Nickel(soluble compounds, insoluble inorganic compounds),

CAS No. 7440-02-0)

- Aluminium

ACGIH: A4

- Cobalt lithium dioxide

IARC: Group 2B (Cobalt and cobalt compounds)

NTP: R (Cobalt compounds)

OSHA: Present (Cobalt compounds)

ACGIH: A3 (Cobalt inorganic compounds)

KOREA-ISHL: Carcinogenicity2 (Cobalt inorganic compounds)

Revision no.: 01

- Polyethylene

IARC: Group 3

- Graphite

IARC: Group 3

- Nickel

IARC: Group 2B (Nickel, metallic and alloys)

NTP: R

OSHA: Present ACGIH: A5

KOREA-ISHL: Carcinogenicity2 (metal) EU Regulation 1272/2008: Carc.2

- 1-Propene, homopolymer

IARC: Group 3 - Nickel sulphide

IARC: Group 1 (Nickel compounds)

NTP: R (Nickel compounds)

OSHA: Present (Nickel compounds)

ACGIH: A1 (Nickel insoluble inorganic compounds), A4 (Nickel soluble inorganic compounds)

KOREA-ISHL: Carcinogenicity1A (Nickel(soluble compounds, insoluble inorganic compounds),

CAS No. 7440-02-0)

- Carbon black

IARC: Group 2B OSHA: Present ACGIH: A3

KOREA-ISHL: Carcinogenicity2 - 1,3 Butadiene/styrene copolymers

IARC: Group 3

- Aluminum lithium oxide (AlLiO)

IARC: Group 1 (Aluminium production)
OSHA: Present (Aluminium production)

ACGIH: A4 (Aluminum insoluble compounds)

SAMSUNG SDI

Mutagenicity: Not classified

- Carbon : Negative reactions were observed in in vitro test(Bacterial Reverse Mutation Assay(OECD Guideline 471, GLP)).
- Iron : Negative reactions were observed in in vitro test(Bacterial Reverse Mutation Assay(OECD Guideline 471, GLP))
- Copper : Negative reactions were observed in in vivo test(mammalian somatic cell study: cytogenicity/erythrocyte micronucleus(EU Method B.12, GLP)).

Revision no.: 01

- Aluminium : Negative reactions were observed in both in vivo (Mammalian Erythrocyte Micronucleus Test(OECD Guideline 474, GLP)) and in vitro (Mammalian cell gene mutation test(OECD Guideline 476, GLP)).
- Cobalt lithium dioxide: Negative reactions were observed in in vitro tests(Bacterial Reverse Mutation Assay(OECD Guideline 471, GLP) and Mammalian cell gene mutation Test(OECD Guideline 476, GLP))(WoE). Negative reactions were observed in in vivo tests(Mammalian Bone Marrow Chromosome Aberration Test(OECD Guideline 475) and Mammalian Erythrocyte Micronucleus Test(OECD Guideline 474, GLP)).
- Dimethyl carbonate: Negative reactions were observed in in vivo (Mammalian Spermatogonial Chromosome Aberration Test (OECD Guideline 483, GLP))
- Polyethylene : No toxicity was observed in in vitro mutagenicity test using Salmonella typhimurium strain.
- Ethylene carbonate : Negative reactions were observed in vitro (Bacterial Reverse Mutation Assay(OECD Guideline 471, GLP)).
- Lithium hexafluorophosphate(1-): Negative reactions were observed in both in vivo (Mammalian Erythrocyte Micronucleus Test(OECD Guideline 474)) and in vitro (Bacterial Reverse Mutation Assay(OECD Guideline 471, GLP)).
- Graphite : Negative reactions were observed in in vitro test(Bacterial Reverse Mutation Assay(OECD Guideline 471, GLP)).
- Ethyl methyl carbonate : Negative reactions were observed in vitro (Mammalian Chromosome Aberration Test (OECD Guideline 473, GLP))
- 1-methyl-2-pyrrolidone: Negative reactions were observed in in vitro tests(Bacterial Reverse Mutation Assay(OECD Guideline 471), Mammalian Gene Mutation Test(OECD Guideline 476, GLP) and DNA Damage and/or Repair Study(OECD Guideline 482, GLP)).
- Negative reactions were observed in in vivo tests(Mammalian Erythrocyte Micronucleus Test(OECD Guideline 474, GLP) and Mammalian Bone Marrow chromosome Aberration Test(OECD Guideline 475, GLP)).
- Nickel sulphide: Posiive reactions were observed in in vivo mammalian germ cell study.(Read-across)
- Silicon : Negative reactions were observed in both in vivo (Mammalian Bone Marrow Chromosome Aberration Test(OECD Guideline 475, GLP))
- Trade secret 2 : Negative reactions were observed in in vivo (Mammalian Erythrocyte Micronucleus Test(OECD Guideline 474, GLP)).
- Lithium carbonate : Negative reactions were observed in in vivo genetic toxicity test.
- Carbon black: Positive reactions were observed in both in vitro (Chromosomal aberrations test (OECD Guideline 476, GLP)) and in vivo (ypoxanthine-guanine phosphoribosyl transferase gene (hprt) mutations in alveolar epithelial cells).
- Succinonitrile: Negative reactions were observed in in vitro tests(Bacterial Reverse Mutation Assay(OECD Guideline 471, GLP) and Mammalian Chromosome Aberration Test(OECD Guideline

Revision no.: 01

SAMSUNG SDI

473, GLP)). Negative reactions were observed in in vivo tests(Mammalian Erythrocyte Micronucleus Test(OECD Guideline 474, GLP))

Reproductive toxicity: Not classified

- Copper: In the reproductive toxicity and developmental toxicity test with rats, there were no significant adverse effects on reproductive parameters and no evidence of malformations at any doses. (OECD Guideline 416, 414, GLP)
- Aluminium : In the reproductive toxicity and developmental toxicity test using rats, adverse effects were not observed, respectively. (OECD Guideline 422, GLP)(OECD Guideline 414)
- Cobalt lithium dioxide: In the reproductive toxicity and developmental toxicity screening tests with rats, treatment with 300 mg cobalt powder/kg bw/day resulted in an increase of the post-implantation loss and a decrease in the live birth index. Treatment with 30 mg cobalt powder/kg bw/day resulted that the mean litter weight of pups was slightly reduced in a dose-related way (not significant at p \leq 0.01), significant only at 300 mg cobalt powder/kg bw/day. (NOAEL(P, F1) = 30 mg/kg bw/day) (OECD Guideline 422, GLP)
- Dimethyl carbonate: In the reproductive toxicity test using rats, adverse effects were not observed, respectively. (OECD Guideline 415, GLP)
 In the developmental toxicity test using rabbits, adverse effects were not observed, respectively. (OECD Guideline 414, GLP)
- Ethylene carbonate: In the reproductive toxicity test using mouse, adverse effects were not observed, respectively. (GLP) In the developmental toxicity test using rabbits, adverse effects were not observed, respectively. (GLP)
- Lithium hexafluorophosphate(1-): In the reproductive toxicity and developmental toxicity test using rats, adverse effects were not observed, respectively. (OECD Guideline 416, GLP)(OECD Guideline 414)
- Graphite : In the reproductive toxicity with rats, there were no significant adverse effects on reproductive parameters. (OECD Guideline 422, GLP)
- Ethyl methyl carbonate: In the reproductive toxicity and developmental toxicity test using rats, adverse effects were not observed, respectively. (OECD Guideline 414)
- Nickel: In the reproductive toxicity and developmental toxicity test with rats, the number of live pups/litter was significantly decreased, pup mortality was significantly increased, and average pup body weight was significantly decreased at the 500 ppm dose level. (OECD Guideline 416, GLP)
- 1,4-Benzenedicarboxylic acid, 1,4-dimethyl ester, polymer with 1,4-cyclohexanedimethanol and 1,2-1-methyl-2-pyrrolidone: In the two-generation reproductive toxicity test with rats, developmental toxicity was evidenced by increased pup mortality and reduced body weight gain, including corresponding effects in the investigated organs, in pups treated at 500/350 mg/kg bw/day. (NOAEL(F) = 160 mg/kg bw/day) (OECD Guideline 416, GLP)
- Nickel sulphide: In the reproductive toxicity with rats, the 500 ppm dose caused significant body weight depression of both mothers and pups and increased neonatal mortality during the postnatal development period. (equivalent or similar to OECD Guideline 416, GLP) (Nickel Chloride Hexahydrate (7791-20-0)).
- Silicon: In the reproductive toxicity and developmental toxicity test using rats, adverse effects were not observed, respectively. (equivalent or similar to OECD Guideline 478) (Read-across; FDA-Compound 71-41 = Silene, calcium silicate (hydrated))
- Lithium carbonate : In the reproductive toxicity test with rats, no toxicological significant changes were detected. (OECD Guideline 416, GLP)

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019 Revision no.: 01

MODEL INR18650-25R



SAMSUNG SDI

- Carbon black: In the reproductive toxicity and developmental toxicity test using mice, adverse effects were not observed, respectively. (OECD Guideline 414, GLP)
- Succinonitrile: In the reproductive toxicity and developmental toxicity tests with rats, there were no significant adverse effects on reproductive parameters. (OECD Guideline 416, GLP)

Specific target organ toxicity (single exposure): Not classified

- Carbon: In the acute oral toxicity test with rats, Animals visible exhibited labored breathing and intermittent gasping. (OECD Guideline 403)
- Iron: In the acute oral toxicity test with rats, inactivity and depression of the animals within a few minutes after administration.(OECD Guideline 401, GLP)
- Copper: In the acute oral toxicity test with rats, clinical signs observed included lethargy, prostrate posture, green coloured diarrhoea, voiding few faeces and moribundity. (OECD Guideline 401, GLP) In the acute inhalation toxicity test with rats, slight to moderate ataxia, slight to moderate tremor and slight to moderate dyspnoea were observed. (OECD Guideline 436, GLP)
- Aluminium: In the acute oral toxicity test using rats, adverse effects were not observed, respectively. (Read-across)(OECD Guideline 401) In the acute inhalation toxicity test using rats, adverse effects were not observed, respectively. (OECD Guideline 403)
- Cobalt lithium dioxide: In the acute toxicity tests with rats, there were no signs of gross toxicity, adverse pharmacologic effects, or abnormal behaviour. (OECD Guideline 425, 402, GLP)
- Dimethyl carbonate: In the acute oral toxicity test using rats, hypoactivity, ataxia and loss of the righting reflex were observed. (OECD Guideline 401, GLP) In the acute dermal toxicity test using rabbits, adverse effects were not observed, respectively. (GLP) In the acute inhalation toxicity test using rats, adverse effects were not observed, respectively. (OECD Guideline 403, GLP)
- Ethylene carbonate: In the acute dermal/inhalation toxicity test using rats, adverse effects were not observed, respectively. (OECD Guideline 402, GLP)(OECD Guideline 403)
- Lithium hexafluorophosphate(1-): In the acute oral toxcity test with rats, lethargy, hunched posture, uncoordinated movements, piloerection were observed. (OECD Guideline 423, GLP)
- Graphite: In the acute oral toxicity test with rats, no signs of discomfort or toxicity effects. (OECD Guideline 423, GLP)
- Ethyl methyl carbonate: In the acute oral and inhalation toxicity test using rats, ataxia, hunched posture, lethargy, decreased respiratory rate and laboured respiration are observed. (OECD Guideline 401, GLP) (OECD Guideline 403, GLP)
- Nickel: In the acute oral toxicity test with rats, no signs of discomfort or toxicity effects. (OECD Guideline 423, GLP)
- 1-methyl-2-pyrrolidone: In the acute oral toxicity test with rats, ataxia and diuresis(4,150 mg/kg bw) were observed. (OECD Guideline 401)
- Nickel sulphide: In the acute inhalation toxicity test with rats, facial staining, ocular discharge, hypoactivity, a thin appearance, hunched posture, reduced fecal volume, cold limbs, and/or reduced food consumption was observed after dosing. (OECD Guideline 403, GLP) (Read-across; Nickel subsulfide)
- Silicon: In the acute oral/dermal toxicity test using rats, adverse effects were not observed, respectively. (OECD Guideline 401, GLP)
- Trade secret 2: In the acute oral toxicity test with rats, piloerection, hypoactivity were observed during the 1st and 2nd step(300 mg/kg), convulsion, labored breathing immediately after dosing and then were found dead within 4 hours after dosing at the 3rd step(2,000 mg/kg). (OECD Guideline 423, GLP)

SAMSUNG

SAMSUNG SDI

- Lithium carbonate: In the acute inhalation toxicity test with rats, both increased secretory responses and labored breathing were observed. (OECD Guideline 403, GLP)

Revision no.: 01

- Carbon black: In the acute oral toxicity and acute inhalation toxicity test with rats, adverse effects were not observed, respectively, (OECD Guideline 401, GLP)(OECD Guideline 403)
- Succinonitrile: In the acute oral toxicity test with rats, decrease in locomotor activity, emaciation, and soiled perinea region and mortality(2,000 mg/kg bw) were observed. (OECD Guideline 423, GLP)

Specific target organ toxicity (repeat exposure): Not classified

- Carbon: In the repeated oral toxicity test, Slight lung inflammatory changes based on minimal increases in pulmonary neutrophils. (OECD Guideline 413, GLP)
- Iron: In the repeated oral toxicity test with rats, the toxic effects include cellular apoptosis or necrosis in heart, spleen and pancreas. (carbonyl iron)
- Copper: In the repeated oral toxicity and inhalation toxicity test using rats, toxicity to organs was not observed. (EU Method B.26, GLP)(OECD Guideline 412, GLP)
- Aluminium: In the repeated oral toxicity toxicity tests using rats, toxicity to organs was not observed. (Read-across)(OECD Guideline 422, GLP) In the repeated inhalation toxicity toxicity tests using rats, toxicity to organs was not observed. (OECD Guideline 413)
- Cobalt lithium dioxide: In the repeated oral toxicity test in 90 days with rats, toxicity to organs was not observed. (OECD Guideline 408, GLP)
- Dimethyl carbonate: In the repeated oral toxicity tests using rats, toxicity to organs was not observed. (OECD Guideline 408, GLP)
- Polyethylene: Reported progressive systemic sclerosis in patients repeatedly exposed to chemicals.
- Ethylene carbonate: In the repeated oral toxicity tests using rats, toxicity to organs was not observed. (OECD Guideline 452)
- Graphite: In the repeated oral toxicity test with rats, no signs of discomfort or toxicity effects. (OECD Guideline 422, GLP) In the repeated inhalation toxicity test with rats, in the Graphite high-dose group, clearly adverse effects such as markedly increased incidence of interstitial fibrosis, were seen in the lung. (OECD Guideline 412, GLP)
- Ethyl methyl carbonate: In the repeated oral toxicity test using rats, toxicity to organs was not observed. OECD Guideline 407, GLP)
- Nickel: In the repeated oral toxicity test, metallic nickel is a potent respiratory tract toxicant that directly injures the lung and the nasal tissues of the rat, and produces marked secondary effects in the lung-draining lymph nodes. (OECD Guideline 413, GLP)
- 1-methyl-2-pyrrolidone: In the repeated oral toxicity test in 90 days with rats, a specific target organ for compound-related adverse systemic toxicity was not identified. (OECD Guideline 408, GLP)
- Nickel sulphide: In the repeated inhalation toxcity tests with rats, the test material had similar effects in the respiratory tract in that all produced atrophy of the olfactory epithelium and a chronic inflammation in the lung. (OECD Guideline 413)(Read-across; Ni₃S₂)
- Silicon: In the repeated inhalation toxicity tests in 90 days using rats, repeated inhalation of silicon particles for 90 days did not induce any severe adverse effects in rats. (OECD Guideline 413, GLP)(Jetmilled Silicon)
- Lithium carbonate: In the repeated oral toxicity test for human, toxicity to organs was not observed.
- Carbon black: In the sub-chronic inhalation toxicity test using rats, there was clear evidence of inflammation and some alveolar epithelial cell hyperplasia and fibrosis at the high exposure group. In the mid-exposure group there was evidence of inflammation characterised by accumulation of neutrophils and macrophages within the alveolar spaces.

Revision no.: 01



- Succinonitrile: In the repeated oral toxicity test in 90 days with rats, No abnormal gross pathologocial findings were observed. (OECD Guideline 408, GLP)

Aspiration Hazard: Not available

Section XII – ECOLOGICAL INFORMATION

X This is a product that fulfills a certain function in solid state with specific shape without dischargin g any chemical substance in its use and has no obligation to write (M)SDS. Since this document co ntains the precautions for safe handling related to its materials or chemical substances consisting of this product, please note that these overall information is irrelevant to this product.

12.1 Ecological toxicity

Acute toxicity: Not classified (ATEmix = 0.11 mg/L)

Fish

- Iron: 96hr-LC₀(Danio rerio) > 100000 mg/L (OECD Guideline 203)
- Copper: 96hr-LC₅₀(Oncorhynchus mykiss) = 0.164 mg/L
- Aluminium : 96hr-LC₅₀(*Pimephales promelas*) = 1.16 mg/L (GLP)
- Cobalt lithium dioxide : 96hr-LC₅₀($Oncorhynchus\ mykiss$) = 1.51 mg/L (ASTM) (Read-across; cobalt (II) chloride hexahvdrate)
- Dimethyl carbonate : 96hr-LC₅₀((*Danio rerio*) ≥ 100 mg/L (OECD Guideline 203, GLP)
- Ethylene carbonate : 96hr-LC₅₀(Oncorhynchus mykiss) > 100 mg/L (OECD Guideline 203, GLP)
- Lithium hexafluorophosphate(1-): 96hr-LC₅₀(Oncorhynchus mykiss) = 51 mg/L
- Graphite: 96hr-LC₅₀(Danio rerio) > 100 mg/L (OECD Guideline 203, GLP)
- Ethyl methyl carbonate : 96hr-LC₅₀(Oncorhynchus mykiss) > 100 mg/L (OECD Guideline 203, GLP)
- Nickel: 96hr-LC₅₀(Oncorhynchus mykiss) = 15.3 mg/L (measured)
- 1-methyl-2-pyrrolidone: 96hr-LC₅₀(Oncorhynchus mykiss) > 500 mg/L (OBBA-bulletin No. 33, 1975)
- Nickel sulphide: 96hr-LC₅₀(Danio rerio) = 100~320 mg/L (OECD Guideline 203, GLP)
- Trade secret 2 : 96hr-LC₅₀(*Danio rerio*) = 6~60 mg/L (OECD Guideline 203, GLP)
- Lithium carbonate : $96hr-LC_{50}(Oncorhynchus\ mykiss) = 5.69\ mg/L\ (OECD\ Guideline\ 203)(calculated for lithium ion)$
- Carbon black : 96hr-LC₀(Danio rerio) = 1000 mg/L (OECD Guideline 203, GLP)
- Succinonitrile : 96hr-LC₅₀(*Danio rerio*) > 100 mg/L (OECD Guideline 203, GLP)

Crustacean

- Iron : 48hr-EC₅₀(Daphnia magna) > 100 mg/L (OECD Guideline 202, GLP)
- Copper: 48hr-LC₅₀(Ceriodaphnia dubia) = 0.014 mg/L
- Aluminium : $48hr-LC_{50}(Ceriodaphnia\ dubia) = 0.72 mg/L\ (GLP)$
- Cobalt lithium dioxide : 48hr-LC₅₀(*Ceriodaphnia dubia*) = 0.61 mg/L (USEPA 2002) (Read-across; cobalt (II) chloride hexahydrate)
- Dimethyl carbonate : 48hr-EC₅₀(*Daphnia magna*) > 100 mg/L (OECD Guideline 202, GLP)
- Ethylene carbonate : 48hr-EC₅₀(Ceriodaphnia dubia) = 5,900 mg/L
- Lithium hexafluorophosphate(1-) : $48hr-LC_{50}(Daphnia\ magna) > 100\ mg/L\ (OECD\ Guideline\ 202,\ GLP)$
- Graphite : 48hr-EC₅₀(*Daphnia magna*) > 100 mg/L (OECD Guideline 202, GLP)

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019

MODEL INR18650-25R

SAMSUNG

SAMSUNG SDI

- Ethyl methyl carbonate: 48hr-EC₅₀(Daphnia magna) > 100 mg/L (OECD Guideline 202, GLP)
- Nickel : $48hr-LC_{50}(Ceriodaphnia\ dubia) = 0.0744\ mg/L\ (USEPA\ 2002,\ ASTM\ 2001,\ OECD\ 1984)(measured)$
- 1-methyl-2-pyrrolidone: 24hr-EC₅₀(Daphnia magna) > 1000 mg/L (DIN 38412 Part 11)

Revision no.: 01

- Nickel sulphide: 48hr-EC₅₀(Daphnia magna) = 9.48 mg/L (OECD Guideline 202, GLP)
- Trade secret 2: 48hr-EC₅₀(Daphnia magna) = 8.4 mg/L (OECD Guideline 202, GLP)
- Lithium carbonate : 48hr-EC₅₀(*Daphnia magna*) = 6.24 mg/L (OECD Guideline 202, GLP)(calculated for lithium ion)
- Carbon black: 24hr-EC₅₀(Daphnia magna) > 5600 mg/L (OECD Guideline 202, GLP)
- Succinonitrile: 48hr-EC₅₀(Daphnia magna) > 100 mg/L (OECD Guideline 202, GLP)

Algae

- Copper : 96hr-EC₅₀(Chlamydomonas reinhardtii) = 0.047 mg/L
- Aluminium : 72hr-EC₅₀(Pseudokirchneriella subcapitata) = 0.2 mg/L (OECD Guideline 201, GLP)
- Cobalt lithium dioxide : $72hr-EC_{50}(Pseudokirchneriella\ subcapitata) = 0.144\ mg/L\ (OECD\ Guideline\ 201)\ (Read-across)$
- Dimethyl carbonate : 72hr-EC₅₀($Pseudokirchneriella\ subcapitata$) > 100 mg/L (OECD Guideline 201, GLP)
- Ethylene carbonate : 72hr-EC₅₀($Pseudokirchneriella\ subcapitata$) > 100 mg/L (OECD Guideline 201,GLP)
- Lithium hexafluorophosphate(1-) : 96hr-EC₅₀(*Pseudokirchneriella subcapitata*) > 100 mg/L (OECD Guideline 201, GLP)
- Graphite : 72hr-EC₅₀(Pseudokirchneriella subcapitata) > 100 mg/L (OECD Guideline 201, GLP)
- Ethyl methyl carbonate : 72hr-EC₅₀($Desmodesmus\ subspicatus$) > $62\ mg/L\ (OECD\ Guideline\ 201,\ GLP)$
- Nickel : 72hr-EC₅₀($Pseudokirchneriella\ subcapitata$) = 0.188 mg/L (equivalent or similar to OECD Guideline 201)
- 1-methyl-2-pyrrolidone : 72hr-EC₅₀(Desmodesmus subspicatus) = 600.5 mg/L (DIN 38412 Part9)
- Nickel sulphide : 72hr-EC₅₀(*Pseudokirchneriella subcapitata*) = $0.082\sim0.148$ mg/L (OECD Guideline 201)
- Silicon : 72hr-EC₅₀(*Pseudokirchneriella subcapitata*) = ca. 250 mg/L (OECD Guideline 201) (Readacross)
- Trade secret 2 : 72hr-EC₅₀(*Pseudokirchneriella subcapitata*) = 32 mg/L (OECD Guideline 201, GLP)
- Lithium carbonate : $72hr-EC_{50}(Desmodesmus subspicatus) > 400 mg/L (OECD Guideline 201, GLP)(Li2CO3)$
- Carbon black : 72hr-EC₅₀($Desmodesmus\ subspicatus$) > 10000 mg/L (OECD Guideline 201, GLP)

Chronic toxicity: Not classified

Fish

- Copper: 30day-NOEC(Perca fluviatilis) = 0.188 mg/L (OECD Guideline 204)
- Aluminium: 33day-NOEC(Danio rerio) = 0.0715 mg/L (OECD Guideline 210, GLP)
- Cobalt lithium dioxide : 34day-NOEC(*Pimephales promelas*) = 0.21 mg/L (ASTM 2002) (Read-across; cobalt (II) chloride hexahydrate)
- Lithium hexafluorophosphate(1-): 22day-NOEC(*Pimephales promelas*) = 0.2 mg/L (EPA 540/86, GLP)
- Nickel: 32day-NOEC(Oncorhynchus mykiss) = 0.134 mg/L (measured)
- Nickel sulphide : 28day-NOEC(*Cyprinodon variegatus*) = 21.7 mg/L (ASTM 2004 and APHA 1998, GLP)

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019

MODEL INR18650-25R

ate: Jan 1st, 2019 Revision no.: 01



SAMSUNG SDI

- Lithium carbonate : 34day-NOEC(*Danio rerio*) = 2.87 mg/L (OECD Guideline 210, GLP)(calculated for lithium ion)
- Succinonitrile: 28day-NOEC(Rare Minnow) > 10 mg/L (OECD Guideline 210, GLP)

crustacean

- Copper: 14day-NOEC(Penaeus mergulensis and Penaeus monodon (prawns) = 0.033 mg/L
- Aluminium : 28day-NOEC(*Hyalella azteca*) = 0.0531 mg/L (GLP)
- Cobalt lithium dioxide : 28day-NOEC(*Hyallela azteca*) = 0.00683 mg/L (OECD Guideline 211) (Readacross; Cobalt dichloride dihydrate)
- Dimethyl carbonate : 21day-NOEC(Daphnia magna) = 25 mg/L (OECD Guideline 211, GLP)
- Lithium hexafluorophosphate(1-): 7day-NOEC(Ceriodaphnia dubia) = 2.55 mg/L (EPA/600/4-91/002)
- Nickel : 7day-NOEC($Ceriodaphnia\ dubia$) = 0.0053~0.0153 mg/L (equivalent or similar to EPA/600/4-91/002)(measured)
- 1-methyl-2-pyrrolidone: 21day-NOEC = 12.5 mg/L (OECD Guideline 211, GLP)
- Nickel sulphide: 10day-NOEC = 0.0202 mg/L (OECD Guideline 211)
- Lithium carbonate : 21day-NOEC(Daphnia magna) = 1.7 mg/L (OECD Guideline 211, GLP)
- Succinonitrile: 21day-NOEC(Daphnia magna) = 0.784 mg/L (OECD Guideline 211, GLP)

Algae

- Copper: 19day-NOEC(giant kelp Macrocystis pyrifera) = 0.0102 mg/L
- Cobalt lithium dioxide : 72hr-NOEC(*Pseudokirchneriella subcapitata*) = 0.0322 mg/L (OECD Guideline 201) (Read-across)
- Ethylene carbonate : 72hr-NOEC(*Pseudokirchneriella subcapitata*) = 100 mg/L (OECD Guideline 201,GLP)
- Lithium hexafluorophosphate(1-): 96hr-NOEC(*Pseudokirchneriella subcapitata*) = 22 mg/L (OECD Guideline 201, GLP)
- Graphite: 72hr-NOEC(Pseudokirchneriella subcapitata) ≥ 100 mg/L (OECD Guideline 201, GLP)
- Ethyl methyl carbonate : 72hr-NOEC(*Desmodesmus subspicatus*) = 62 mg/L (OECD Guideline 201, GLP)
- 1-methyl-2-pyrrolidone: 72hr-EC₅₀(Desmodesmus subspicatus) = 672.8 mg/L (DIN 38412 Part9)
- Trade secret 2: 72hr-NOEC(Pseudokirchneriella subcapitata) = 1 mg/L (OECD Guideline 201, GLP)
- Lithium carbonate : 72hr-NOEC(*Desmodesmus subspicatus*) = 9.39 mg/L (OECD Guideline 201, GLP)(calculated for lithium ion)
- Carbon black: 72hr-NOEC(Desmodesmus subspicatus) > 10000 mg/L (OECD Guideline 201, GLP)
- Succinonitrile: 72hr-NOEC(Desmodesmus subspicatus) = 100 mg/L (OECD Guideline 201, GLP)

12.2 Persistence and degradability

Persistence

- Carbon : Low persistency (log K_{ow} is less than 4 estimated.) (log K_{ow} = 0.78) (estimated)
- Dimethyl carbonate : Low persistency (log K_{ow} is less than 4 estimated.) (log K_{ow} = 0.354) (20°C, 6.5 < pH < 7.5)
- Ethylene carbonate : Low persistency (log K_{ow} is less than 4 estimated.) (log K_{ow} = 0.11) (20 °C, 5.33 < pH < 5.79)
- Lithium hexafluorophosphate(1-): Hydrolysis readily in contact with water. According to this it was not possible to determine the partition coefficient. (OECD Guideline 107, GLP)
- Ethyl methyl carbonate : Low persistency (log K_{ow} is less than 4 estimated.) (log K_{ow} = 0.972) (40 °C, EU Method A.8, GLP)
- 1-methyl-2-pyrrolidone : Low persistency (log K_{ow} is less than 4 estimated.) (log K_{ow} = -0.46)

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019

MODEL INR18650-25R

SAMSUNG

SAMSUNG SDI

- Trade secret 2 : Low persistency (log K_{ow} is less than 4 estimated.) (log K_{ow} = -0.435) (OECD Guideline 107, GLP)
- Succinonitrile : Low persistency (log K_{ow} is less than 4 estimated.) (log K_{ow} = -0.99)

Revision no.: 01

Degradability:

- Polyethylene: (1) Polyethylene films incubated in aerobic and anaerobic bioreactors did not degrade over the course of 4-week to 25-week exposure periods. (2) Similar experiments conducted using aerobic and anaerobic bioreactors concluded no biodegradation of polyethylene occurred over 40-70 day incubation periods.

12.3 Bioaccumulative potential

Bioaccumulation

- Carbon : Bioaccumulation is expected to be low according to the BCF < 500 (BCF = 2.433) (estimated)
- Cobalt lithium dioxide : Bioaccumulation is expected to be high according to the BCF \geq 500 (BCF = 5500)
- Dimethyl carbonate: Bioaccumulation is expected to be low according to the BCF < 500 (BCF < 3.2)
- Lithium hexafluorophosphate(1-) : Bioaccumulation is expected to be low according to the BCF < 500 (BCF = $53\sim58$)
- Nickel: Bioaccumulation is expected to be low according to the BCF < 500 (BCF = 45)
- 1-methyl-2-pyrrolidone : Bioaccumulation is expected to be low according to the BCF < 500 (BCF = 3.162) (estimated)
- Nickel sulphide: Bioaccumulation is expected to be low according to the BCF < 500 (BCF = 45)
- Succinonitrile : Bioaccumulation is expected to be low according to the BCF < 500 (BCF = 3.162) (estimated)

Biodegradation

- Dimethyl carbonate: As well-biodegraded, it is expected to have low accumulation potential in living organisms(86% biodegradation was observed after 28 days) (OECD Guideline 301C)
- Ethylene carbonate: As well-biodegraded, it is expected to have low accumulation potential in living organisms(86% biodegradation was observed after 29 days) (OECD Guideline 301B)
- Ethyl methyl carbonate: As well-biodegraded, it is expected to have low accumulation potential in living organisms(98% biodegradation was observed after 28 days) (GLP)
- 1-methyl-2-pyrrolidone: As well-biodegraded, it is expected to have low accumulation potential in living organisms(73% biodegradation was observed after 28 days) (OECD Guideline 301C)
- Trade secret 2: As not well-biodegraded, it is expected to have high accumulation potential in living organisms(65% biodegradation was observed after 28 days) (OECD Guideline 301D, GLP)
- Succinonitrile : As well-biodegraded, it is expected to have low accumulation potential in living organisms(99.4% biodegradation was observed after 14 days) (OECD Guideline 301A, GLP)

12.4 Mobility in soil

- Carbon : No potency of mobility to soil. (K_{oc} = 8.823) (estimated)
- Dimethyl carbonate : No potency of mobility to soil. (K_{oc} = 2.9 ~ 6.65) (25 °C)
- Ethylene carbonate : No potency of mobility to soil. (K_{oc} = 11.9)
- Ethyl methyl carbonate: No potency of mobility to soil. (K_{oc} = 1.58) (OECD Guideline 121, GLP)
- 1-methyl-2-pyrrolidone : No potency of mobility to soil. (K_{oc} = 4.65) (estimated)
- Succinonitrile: No potency of mobility to soil. (K_{oc} = 14.52) (estimated)

12.5 Results of PBT and vPvB assessment : Not applicable

12.6 Other adverse effects: Not available

Revision no.: 01



Section XIII - DISPOSAL CONSIDERATION

13.1 Waste treatment methods

Product/Packaging disposal

- Consider the required attentions in accordance with waste treatment management regulation.

Waste codes / Waste designation according to LoW(2015): 16-06-05

Waste treatment-relevant information

- Waste must be disposed of in accordance with federal, state and local environmental control regulations.

Sewage disposal-relevant information: Not available Other disposal recommendations: Not available

Section XIV – TRANSPORTATION INFORMATION

14.1 UN Number: 3480

14.2 UN Proper shipping name: LITHIUM ION BATTERIES (including lithium ion polymer ba

tteries)

14.3 Transport Hazard class: 9

14.4 Packing group : Ⅱ

14.5 Special provisions: 188, 230, 384
14.6 Packing instructions: P903
14.7 Environmental hazards: No
14.8 Special precautions for user

in case of fire: F-A in case of leakage: S-I

14.9 Transport in bulk according to Annex II of MARPOL 73/78 and the IBC Code: Not

Available

14.10 IATA Transport: PI 965-Section IB

14.11 Package labels

Revision no.: 01





Section XV – REGULATORY INFORMATION

15.1 Safety, health and environmental regulation/legislation specific for the substance or mixture EU regulations

Authorisations and/or restrictions on use:

Authorisations: Not regulated

Restrictions on use:
- Nickel : Regulated

- 1-Methyl-2-pyrrolidinone : Regulated

Other EU regulations:

- 1-Methyl-2-pyrrolidinone : Regulated (SVHC list)

U.S.A regulations

U.S.A management information (OSHA Regulation): Not regulated

U.S.A management information (CERCLA Regulation):

- Copper : 5,000 lb - Nickel : 100 lb

U.S.A management information (EPCRA 302 Regulation): Not regulated **U.S.A management information (EPCRA 304 Regulation)**: Not regulated

U.S.A management information (EPCRA 313 Regulation):

- Copper: Regulated

- Aluminium (metal): Regulated

- Nickel: Regulated

1-Methyl-2-pyrrolidinone : Regulated1-Methyl-2-pyrrolidinone : RegulatedLithium carbonate : Regulated

KOREA regulations

Occupational Safety and Health Act

- Litium nickel oxide: Threshold Limit Values (TLVs) chemicals, Hazardous Substances Subject to Control, Special management materials, Harmful Agents Subject to Work Environment Monitoring (Measurement cycle: 6 Months), Harmful Agents Subject to Workers Requiring Health Examination (Diagnostic cycle: 12 Months), Chemicals subject to permissible exposure limit
- Iron: Threshold Limit Values (TLVs) chemicals, Hazardous Substances Subject to Control
- Copper: Threshold Limit Values (TLVs) chemicals, Hazardous Substances Subject to Control, Harmful Agents Subject to Work Environment Monitoring (Measurement cycle: 6 Months), Harmful Agents Subject to Workers Requiring Health Examination (Diagnostic cycle: 12 Months)
- Lithium nickel dioxide : Threshold Limit Values (TLVs) chemicals, Hazardous Substances Subject to Control, Special management materials, Harmful Agents Subject to Work Environment Monitoring

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019

MODEL INR18650-25R

SAMSUNG

SAMSUNG SDI

(Measurement cycle : 6 Months), Harmful Agents Subject to Workers Requiring Health Examination (Diagnostic cycle : 12 Months), Chemicals subject to permissible exposure limit

Revision no.: 01

- Aluminium: Threshold Limit Values (TLVs) chemicals, Hazardous Substances Subject to Control, Harmful Agents Subject to Work Environment Monitoring (Measurement cycle: 6 Months), Harmful Agents Subject to Workers Requiring Health Examination (Diagnostic cycle: 12 Months)
- Cobalt lithium dioxide: Threshold Limit Values (TLVs) chemicals, Hazardous Substances Subject to Control, Harmful Agents Subject to Work Environment Monitoring (Measurement cycle: 6 Months), Harmful Agents Subject to Workers Requiring Health Examination (Diagnostic cycle: 12 Months)
- Lithium Manganese (III,IV) oxide: Threshold Limit Values (TLVs) chemicals, Hazardous Substances Subject to Control, Harmful Agents Subject to Work Environment Monitoring (Measurement cycle: 6 Months), Harmful Agents Subject to Workers Requiring Health Examination (Diagnostic cycle: 12 Months)
- Graphite: Threshold Limit Values (TLVs) chemicals, Harmful Agents Subject to Work Environment Monitoring (Measurement cycle: 6 Months), Harmful Agents Subject to Workers Requiring Health Examination (Diagnostic cycle: 12 Months)
- Nickel: Threshold Limit Values (TLVs) chemicals, Hazardous Substances Subject to Control, Special management materials, Harmful Agents Subject to Work Environment Monitoring (Measurement cycle: 6 Months), Harmful Agents Subject to Workers Requiring Health Examination (Diagnostic cycle: 12 Months), Chemicals subject to permissible exposure limit
- Nickel sulphide: Threshold Limit Values (TLVs) chemicals, Hazardous Substances Subject to Control, Harmful Agents Subject to Work Environment Monitoring (Measurement cycle: 6 Months), Harmful Agents Subject to Workers Requiring Health Examination (Diagnostic cycle: 12 Months), Chemical substance subject to authorization
- Silicon: Threshold Limit Values (TLVs) chemicals
- Carbon black : Threshold Limit Values (TLVs) chemicals

Chemicals Control Act

- 1-methyl-2-pyrrolidone : Toxic chemicals (2014-1-700, 0.3%)
- Nickel sulphide: Toxic chemicals (97-1-130, 0.1%)
- Succinonitrile: Toxic chemicals (2018-1-816, 25%)

Safety Control of Dangerous Substances Act

- Carbon : Non-dangerous goods
- Iron: Iron content class 2, 500 kg
- Copper: Non-dangerous goods
- Aluminium: Metal powder class 2, 500 kg
- Dimethyl carbonate: Petroleum class 4-1 (non-water soluble liquid), 200 l
- Lithium Manganese (III,IV) oxide: Non-dangerous goods
- Ethylene carbonate : Non-dangerous goods
- Nickel: Non-dangerous goods
- 1-methyl-2-pyrrolidone : Petroleum class 4-3 (water soluble liquid),4,000 ℓ
- Silicon: Metal powder class 2, 500 kg
- Trade secret 2 : Petroleum class 4-3 (non-water soluble liquid), 2000 $\!\ell$
- Lithium carbonate : Non-dangerous goods
- Carbon black : Non-dangerous goods
- Carboxymethyl cellulose sodium salt : Non-dangerous goods

Wastes Control Act

SAMSUNG SDI Co., Ltd. Date: Jan 1st, 2019 Revision no.: 01



SAMSUNG SDI

- 1-methyl-2-pyrrolidone : Controlled wastes (Wastes toxic chemicals)

- Nickel sulphide : Controlled wastes Wastes toxic chemicals)
- Succinonitrile: Controlled wastes Wastes toxic chemicals)

External information:

MODEL INR18650-25R

Substance of Roterdame Protocol: Not regulated Substance of Stockholme Protocol: Not regulated Substance of Montreal Protocol: Not regulated

15.2 Chemical safety assessment:

- No chemical safety assessment has been carried out for this product by the supplier.

Section XVI – OTHER INFORMATION EU

Product safety data sheet for PA0001N0006A/PA0001N0007A/PA001N0008A prepared in accordance with Regulation (EU) 2015/830 (REACH), Annex II, and OSHA 29 CFR 1910.1200

16.1 Indication of changes

Date Updated: 01 Feb. 2019

Version: Rev. 01

16.2 Abbreviations and acronyms

ACGIH = American Conference of Government Industrial Hygienists

CLP = Classification Labelling Packaging Regulation; Regulation (EC) No 1272/2008

CAS No. = Chemical Abstracts Service number

DMEL = Derived Minimal Effect Levels

DNEL = Derived No Effect Level

EC Number = EINECS and ELINCS Number (see also EINECS and ELINCS)

EU = European Union

IARC = International Agency for Research on Cancer

ISHL = Industrial Safety & Health Law

NIOSH = National Institute for Occupational Safety & Health

NTP = National Toxicology Program

OSHA = European Agency for Safety and Health at work

PBT = Persistent, Bioaccumulative and Toxic substance

PNEC(s) = Predicted No Effect Concentration(s)

REACH = Registration, Evaluation, Authorisation and Restriction of Chemicals Regulation (EC) No 453/2010

STP = Sewage Treatment Plant

SVHC = Substances of Very High Concern

vPvB = Very Persistent and Very Bioaccumulative

UN = United Nations

MARPOL = International Convention for the Prevention of Pollution from Ships (IMO)

IBC = Intermediate Bulk Container

CERCLA = Comprehensive Environmental Response, Compensation & Liability Act (US)

EPCRA = Emergency Planning and Community Right-to-Know Act (US)

SAMSUNG SDI Co., Ltd.
Date: Jan 1st, 2019 Revision no.: 01

MODEL INR18650-25R

SAMSUNG

SAMSUNG SDI

EINECS = European Inventory of Existing Commercial chemical Substances

ELINCS = European List of Notified Chemical Substances

16.3 Key literature reference and sources for data :

UN Recommendations on the transport of dangerous goods 17th

Emergency Response Guidebook 2008;

http://phmsa.dot.gov/staticfiles/PHMSA/DownloadableFiles/Files/erg2008 eng.pdf

EU CLP; https://echa.europa.eu/information-on-chemicals/cl-inventory-database

REACH information on registered substances; https://echa.europa.eu/information-on-

chemicals/registered-substances

U.S. National library of Medicine (NLM) Hazardous Substances Data Bank(HSDB);

http://toxnet.nlm.nih.gov/cgi-bin/sis/htmlgen?HSDB

OECD SIDS; http://webnet.oecd.org/hpv/ui/Search.aspx

ECOTOX; http://cfpub.epa.gov/ecotox/

EPISUITE v4.11; https://www.epa.gov/tsca-screening-tools/download-epi-suitetm-estimation-program-

interface-v411

Chemicalbook; http://www.chemicalbook.com/ProductIndex EN.aspx

LookChem; http://www.lookchem.com/ Chemblink;http://www.chemblink.com/

SIGMA-ALDRICH; http://www.sigmaaldrich.com/united-states.html

Chemspider; http://www.chemspider.com/

IARC Monographs on the Evaluation of Carcinogenic Risks to Humans; http://monographs.iarc.fr

National Toxicology Program; http://ntp.niehs.nih.gov/results/dbsearch/

TOMES-LOLI®; http://www.rightanswerknowledge.com/loginRA.asp

American Conference of Governmental Industrial Hygienists TLVs and BEIs.

The Chemical Database -The Department of Chemistry at the University of Akron

EPA-IRIS; http://www.epa.gov/ncea/iris/index.html

NIOSH Pocket Guide; http://www.cdc.gov/niosh/npg/npgdcas.html

Korea Occupational Health & Safety Agency; http://www.kosha.or.kr

National Chemicals Information System; http://ncis.nier.go.kr/main.do

Ministry of Public Safety and Security-Korea dangerous material inventory management system;

http://hazmat.mpss.kfi.or.kr/index.do

Waste Control Act enforcement regulation attached [1]

16.4 Classification and procedure used to derive the classification for mixtures according to

Regulation(EC) 1272/2008(CLP): Not classified

16.5 Relevant H-statements: Not applicable

16.6 Training advice:

Do not handle until all safety precautions have been read and understood.

16.7 Further information :

Data of sections 4 to 8, as well as 10 to 12, do not necessarily refer to the use and the regular handling of the product (in this sense consult package leaflet and expert information), but to release of major amounts in case of accidents and irregularities. The information describes exclusively the safety requirements for the product (s) and is based on the present level of our knowledge. This data does not constitute a uarantee for the characteristics of the product(s) as defined by the legal warranty regulations. "(n.a. = not applicable; n.d. = not determined)"